



SMO1

| | |
|---|---|
| PRODUCT CODE | SLIP/KK/SMO8 |
| BRICK TYPE | Clay brick slip |
| SPECIFICATION | Manufactured to BS EN 14411:2012 |
| SIZE | 65 x 215 x 14mm |
| DIMENSIONAL TOLERANCE | |
| <ul style="list-style-type: none"> • LENGTH & WIDTH • THICKNESS • SQUARENESS • SURFACE FLATNESS • CURVATURE OF SIDES | <ul style="list-style-type: none"> ±2.0% to maximum ±4mm ±10% ±1.0% ±1.5% ±1.0% |
| SURFACE QUALITY | Minimum 95% of slips should not have visible defects causing deterioration of the appearance. |
| FLEXURAL STRENGTH | ≥ 13 N/MM ² |
| BREAKING FORCE | ≥ 800N |
| THERMAL SHOCK RESISTANCE | Yes |
| REACTION TO FIRE | Class A1 |
| WATER ABSORPTION | ~ 3% |
| FROST RESISTANCE | Yes |
| PACKAGING | Shrink wrapped on wooden pallets. |
| PACK SIZE: L X W X H | 1100 x 1100 x 1100mm Approx. |
| PACK WEIGHT | 1.2 Tonnes Approx. |
| USAGE | Always mix from several packs. |
| PERFORMANCE | The recommendations of good practice made in the relevant British Standards regarding design and workmanship must be fully observed. Liability cannot be accepted for the performance of the product if used outside our recommendations. |
| DOP COMMON ROOT REF CODE | No. 1/2023 of 19.05.2023 |



BRICK SLIPS
BY IMPERIAL BRICKS

For more information on products, services, advice and technical guidelines please contact our sales team.
01746 330994 • brickslips@imperialbricks.co.uk • www.brickslips.imperialbricks.co.uk

Individual brick slips may vary dimensionally; this is a natural characteristic of fired clay brick slip and is catered for in BS EN 14411:2012
Technical data correct at time of issue as provided by manufacturer. Always order samples before purchasing and follow good practice guidelines.



Sedex Member



VERISIO

LUCIDEON

providing material solutions

